



412 Prescott Street
Greensboro, NC 27401

2115 Frank Bird Blvd.
Rockford, TN 37853

Call: 1-888-331-9991

8 Mil Reinforced Poly Spec Sheet

<u>PROPERTY</u>	<u>TEST METHOD</u>	<u>SPECS</u>
Thickness, Nominal		8 Mils.
Weight, Average	ASTM D-751	37 lbs./msf
Grab Tensile Elongation (At break)	ASTM D-7004	72%
Grab Tensile (Average of Directions)	ASTM D-7004	60 lbs
Tongue Tear Resistance (Average of Directions)	ASTM D-5884	36 lbs.
Mullen Burst	ASTM D-751	133 psi
CBR Puncture Strength	ASTM D-6241	218 lbs.
WVTR	ASTM E-96 (Procedure B)	0.0167
Perm Rating	ASTM E-96 (Procedure B)	0.04 Perms

Properties represented are typical and not intended as specification limits.

MD = Machine Direction

TD = Transverse Direction

SKU#Li-MC08WB1200